

TECH DATA SHEET

PROJOINT

V35-UV

100% UV STABLE PU RESIN PAVING GROUT

PREPARATION:


ENSURE THE SURFACE OF THE PAVING IS CLEAN PRIOR TO APPLICATION. CHECK THE JOINTS ARE CLEANED OUT TO A DEPTH OF 25MM FOR 3.5 TONNES TRAFFIC LOADING, OBSERVING A MINIMUM JOINT WIDTH OF 5MM. PAVING SHOULD BE FIRMLY BEDDED AND STABLE PRIOR TO FILLING JOINTS AND LAID ON BEDDING MATERIAL SUITABLE FOR THE INTENDED TRAFFIC LOADING. PROJJOINT V35-UV CAN BE INSTALLED ON PAVING WITH EITHER A PERMEABLE OR NON-PERMEABLE BEDDING. FOR SENSITIVE/SAWN PAVING WE RECOMMEND USING OUR PROJJOINT PRE-GROUT SEALER PRIOR TO APPLICATION. WE RECCOMEND A SMALL TEST AREA PRIOR TO USE. SUITABLE ONLY FOR NATURAL STONE AND CONCRETE PAVING.

APPLICATION INSTRUCTIONS:

APPLY PROJJOINT V35-UV WHEN THE SURFACE TEMPERATURE IS BETWEEN 0°C AND 25°C.

1: ENSURE SURFACE IS CLEAN AND READY TO WORK WITH. 2: EMPTY THE SAND INTO A SUITABLE MIXING VESSEL, THEN WHEN WEARING APPROPRIATE PPE, ADD THE RESIN AND BEGIN MIXING USING A MIXING PADDLE. CONTINUE MIXING FOR AROUND THREE MINUTES UNTIL THOROUGHLY MIXED 3: EMPTY THE MIX ONTO THE PAVING AND WORK INTO THE JOINTS USING A SOFT/MEDIUM BRUSH OR SQUEEGEE. ENSURING THE MATERIAL IS WELL COMPACTED INTO THE JOINTS AS ANY UNDERLYING VOIDS COULD RESULT IN SECONDARY SETTLEMENT 4: ONCE WORKED INTO THE JOINTS, USE A SOFT BRUSH AT 45° ANGLE TO CAREFULLY SWEEP OFF ALL THE EXCESS LEAVING THE AREA CLEAN.

AVAILABLE IN THREE COLOURS



NEUTRAL BUFF MID-GREY



BLACK

HEALTH AND SAFETY ADVISORY



DANGER

PROJJOINT V35-UV IS NOT A TOXIC PRODUCT. HOWEVER CARE SHOULD BE TAKEN NOT TO INGEST THIS PRODUCT. IF INGESTED SEEK MEDICAL ATTENTION IMMEDIATELY. IF PRODUCT GETS INTO EYES RINSE THOROUGHLY WITH WATER AND SEEK MEDICAL ATTENTION.

KEY FACTS:

- ✓ ONE PART RESIN BASED MORTAR SYSTEM, CEMENT FREE
- ✓ TOLERATES LOADS UP TO 3.5 TONNES
- ✓ FAST APPLICATION, NO BENDING OR KNEELING
- ✓ HIGH STRENGTH AND SUITABLE FOR JOINT WIDTHS 5MM UPWARDS
- ✓ UV STABLE, WEED,PRESSURE WASHER AND FROST RESISTANT
- ✓ LONG WORKING TIME IDEAL FOR NARROW JOINTS AND HOT WEATHER
- ✓ PROFESSIONAL RESULTS; NO MESS AND NO RETURNING FOR CLEANING

BRUTE STRENGTH PAVING PRODUCTS

DISCOVER MORE: CALL: 01937 858000 | SALES@NEXUSPROSYSTEMS.CO.UK | WWW.NEXUSPAVINGSYSTEMS.CO.UK



APPLICATION IMAGERY

SYSTEM	1-PART PU RESIN MORTAR SYSTEM
STORAGE	STORE IN A COOL, DRY, AND FROST FREE ENVIRONMENT AT TEMPERATURES BETWEEN 5°C AND 30°C
SHELF LIFE	12 MONTH FROM DATE OF MANUFACTURE
PACKAGING	26KG KIT - 1KG RESIN TIN AND 25KG SAND BAG
COVERAGE	AS SHOWN ON COVERAGE TABLE
COLOURS	NEUTRAL, MID-GREY, BLACK
WALK ON CURING TIME	12 HOURS IN DRY AMBIENT CONDITIONS
VEHICLE ON CURING TIME	24 HOURS IN DRY AMBIENT CONDITIONS
FULL STRENGTH	28 DAYS
SUB BASE REQUIREMENT	FULL SOLID BED WITH A PERMEABLE BEDDING OR NON-PERMEABLE BEDDING MORTAR, AS SPECIFIED FOR INTENDED USE.

APPROXIMATE COVERAGE PER 26KG KIT

Joint Size	600x600mm slabs	Four size Indian (600mm series)	100x100mm setts
5 x 25mm	45m ²	39m ²	7.6m ²
10 x 25mm	22.5m ²	19.5m ²	3.8m ²
15 x 25mm	15m ²	13m ²	2.5m ²

HEALTH & SAFETY ADVISORY: RESIN COMPONENT

Restricted to professional users.

Please refer to these user instructions for correct product usage.

Contains: Hexamethylene-1,6-diisocyanate, Homopolymer xylene dibutyltin dilaurate.

Hazard statements: H317 May cause an allergic skin reaction. H332 Harmful if inhaled. H335 May cause respiratory irritation.

Precautionary statements: P261 Avoid breathing dust/fume/gas/mist/vapours/spray. P280 Wear protective gloves/protective clothing/eye protection/face protection. P333+P313 If skin irritation or rash occurs: Get medical advice/attention. P362+ P364 Take off contaminated clothing and wash it before reuse. P312 Call a POISON CENTER/doctor if you feel unwell.

EUH204 contains isocyanates. May produce an allergic reaction. For full safety information, refer to MSDS.

